


1,2-SBS

(Development material)

Styrene/Butadiene/Styrene
produced by NIPPON SODA



1,2-SBS	Contents (wt%) o/p/q	Mn	1,2-Vinyl ratio(%) m/(m+n)	Viscosity (P@45°C)
Solid type	25/50/25	<30,000	≥90	-
Liquid type	10/80/10	5,000	≥90	1000



Solid type



Liquid type

**High content of 1,2-Vinyl units contribute
to co-crosslinking functionality.**

Samples are currently available!

Contact us at chemical@nissoamerica.com for further information or samples.